



Vitafoam Magyarország Kft. / Vitafoam Hungary Ltd.
 Vita Comfort Foams division of The Vita Group
 Registered office / Székhely: H-7030 Paks, Hrsz: 8806/2 (Ipari Park)
 Registered No. / Cg. 17-09-006137
 Tel.: 00 36 75 519 701
 Fax: 00 36 75 519 a
 e-mail: laboratory@vitahungary.hu

VASCO POLIURETÁN HAB
 VASCO POLYURETHANE FOAM GRADE
 SPUME VASCOELASTICE

VISCO ELASTICNE PIENE

Fizikai tulajdonságok Foam properties Proprietati fizice Fizikalna svojstva Proprietăți fizice Physische eigenschaft	VA4015	VA5015	VA5020	VA6020	Alkalmazott szabvány Test method Metoda de testare Metoda testiranja Test Prozedur
Sűrűség [ka/m ³] Density [ka/m ³] Densitate [ka/m ³] Netto gustoća [ka/m ³] Densită [ka/m ³] Netto R.G. [ka/m ³]	35-45	48-53	48-53	57-62	ISO 845 : 1988
Keménység / Rezistenta la comprimare / Tvrdóca/Durezza /Härte CLD, 40 % [kPa]	1,0-2,0	1,1-1,7	1,5-2,5	1,4-2,2	ISO 3386/1 : 1986
ILD, 25 % [N] ILD, 40 % [N] ILD, 65 % [N]					ISO 2439:2008 method B ISO 2439:2008 method B ISO 2439:2008 method B
Hardness, 25 % [N] Hardness, 65 % [N] Hardness, 25 % Recovery [N]					IO 14 - Internal Method IO 14 - Internal Method IO 14 - Internal Method
Support factor Thickness loss by fatigue % maximum Hardness loss by fatigue % maximum Resilience, %					ISO 3385:1989 ISO 3385:1989 ISO 38307: 1990
Szakítószilárdság , minimum [kPa] Tensile strength, minimum [kPa] Rezistenta la Rupere , minimum [kPa] Elasticnost Resistenza a trazione, minimum [kPa] Zuqfestigkeit, minimum [kPa]	40	40	40	40	ISO 1798 : 1997
Szakadási nyúlás , minimum [%] Elongation at break, minimum [%] Alungirea la rupere, minim [%] Prekidna čvrstoća, minimum [%] Allungamento alla rottura, minimum [%] Dehnung beim Bruch, minimum [%]	150	150	150	150	ISO 1798 : 1997
Maradandó összenyomódás 75 % , maximum [%] Compression set at 75%, maximum [%] Deformarea remanenta la 75%, [%] Trajna deformacija, maximum [%] Deformazione residua dopo compressione, maximum [%] Druckverformungsreset at 75%, maximum [%]	7	7	7	7	ISO 1856 : 2000
Standard szín Standard colour Culoare Boja Colore Farben	zöld green verde zelená grün	sárga yellow galben zuta gelb	sárga yellow galben zuta gelb	fehér white alb bijela weiss	